



106 KILGORE RD.  
 CARROLLTON, GA 30116  
 1-888-5-URE-TEC  
 WWW.URE-TEC.COM

## PRODUCT DATA – BPL 7100

### DESCRIPTION

**BPL 7100** is a 100% polyurea spray elastomer with exceptional physical properties. Its instantaneous reactivity and one-to-one ratio makes **BPL 7100** an excellent choice for high performance applications.

### PROPOSED USES

**BPL 7100** is designed for use in harsh environments where high temperature, chemical, and/or abrasion resistance is needed. Tank coatings and chemical containment are examples of where this product should be used.

### TYPICAL PROPERTIES

Property	Test Method	“A”	“B”
Color	N/A	Off-white	Amber/ Black
Specific Gravity	ASTM D-1638	1.12	1.08
Viscosity	Brookfield LVF	900 cps +100	1000 cps + 100
Mixing Ratio	By Volume	50	50
Pounds Per Gallon	From Spec. Gravity	10.3	8.3

### PHYSICAL PROPERTIES

<b>DENSITY (PCF)</b>	<b>(ASTM D-1622)</b>	<b>70</b>
<b>SHORE A HARDNESS</b>	<b>(ASTM D-2240)</b>	<b>90 - 95</b>
<b>SHORE D HARDNESS</b>	<b>(ASTM D-2240)</b>	<b>60</b>
<b>TENSILE STRENGTH</b>	<b>(ASTM D-2370)</b>	<b>2900 psi minimum</b>
<b>ELONGATION</b>	<b>(ASTM D-2370)</b>	<b>225% minimum</b>
<b>TEAR STRENGTH</b>	<b>(ASTM D-1004)</b>	<b>550 ppi minimum</b>
<b>TABER ABRASION (H-18 WHEEL, 1000 CYCLES)</b>		<b>0.013% weight loss</b>

Call Ure-Tec for technical questions. 888-5-URE-TEC

THE INFORMATION HEREIN IS BELIEVED TO BE RELIABLE, BUT UNKNOWN RISKS MAY BE PRESENT. URE-TEC WARRANTS ONLY THAT THE MATERIALS SHALL BE OF MERCHANTABLE QUALITY. THIS WARRANTY IS IN LIEU OF ALL OTHER WRITTEN OR UNWRITTEN, EXPRESSED OR IMPLIED WARRANTIES URE-TEC., EXPRESSLY DISCLAIMS ANY WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, OR FREEDOM FROM PATENT INFRINGEMENT. ACCORDINGLY, BUYER ASSUMES ALL RISKS WHATSOEVER AS TO THE USE OF THESE MATERIALS. BUYER'S EXCLUSIVE REMEDY AS TO ANY BREACH OF WARRANTY OR NEGLIGENCE CLAIM SHALL BE LIMITED TO THE PURCHASE PRICE OF THE MATERIALS. FAILURE TO STRICTLY ADHERE TO RECOMMENDED PROCEDURES SHALL RELIEVE URE-TEC OF ALL LIABILITY WITH RESPECT TO THE MATERIALS OR THE USE THEREOF.